

WallpaperSol Persomural 195

■ matt 3280 - 195 g/m²

High Quality non-woven wallpaper coated with a solvent ink compatible inkjet layer, which offers a good colour gamut and high scratch resistance. Due to the properties of this wallpaper, no additional protection is needed and it can be hung with standard non-woven wallpaper paste.

Applications

- Interior design

Advantages

- The coating and prints are water-resistant - no liquid lamination required
- Quick dry
- Smooth surface with satin finishing
- Wide gamut and high colour rendering
- High opacity for good coverage
- High dimensional stability and wet strength resistance
- Can be applied with standard paste for non-woven wallpaper
- Can cover small cracks
- Easy to remove
- PVC-free
- [Fire Classification: C-s1,d0 \(ISO EN 13501-1:2007\)](#)

WallpaperSol Persomural 195

■ matt 3280 - 195 g/m²

List of Printers

Printer	Ink	Quality
Hewlett Packard DJ L65500 Latex ink	Inkjet mit IR- / Latex Tinte	Excellent
Hewlett Packard DJ L25500 / 26500 / 28500 - Latex 260 / 280	Inkjet mit IR- / Latex Tinte	Excellent
Hewlett Packard Scitex LX 600	Inkjet mit IR- / Latex Tinte	Excellent
Hewlett Packard Scitex LX 800 / LX 820 / LX 850	Inkjet mit IR- / Latex Tinte	Excellent
Epson Stylus Pro GS6000 UltraChrome GS	Inkjet mit Eco Solvent	Excellent
Epson SureColor SC-30600 / 50600 / 70600	Inkjet mit Eco Solvent	Excellent
Roland SolJet SJ540 / SC540 SJ 740 / SC740	Inkjet mit Eco Solvent	Excellent
Roland SC-500 Permasol S	Inkjet mit Lösemitteltinte	Excellent
Roland VersaCAMM SP-300i / SP-540i	Inkjet mit Eco Solvent	Excellent
Roland VersaCAMM VP-300i / VP-540i	Inkjet mit Eco Solvent	Excellent
Roland VS 540 / VS 640	Inkjet mit Eco Solvent	Excellent
Roland CJV 30	Inkjet mit Eco Solvent	Excellent
Roland SolJET PRO4 XR-640	Inkjet mit Lösemitteltinte	Excellent
Océ CS9360 / CS935	Inkjet mit Eco Solvent	Excellent

Last update: 01.01.1900

WallpaperSol Persomural 195

■ matt 3280 - 195 g/m²

Physical Properties

Weight (Total) [gsm]	195	ISO 536
Thickness (total) [microns]	340	ISO 534
Chromaticity (D65 / 10°)	L* 97 a*-0,5 b*3,5	DIN 6174
Opacity [%]	91	ISO 2471
Whitiness (CIE, D65/2°)	75	CIELab System

Recommended use and storage

To maintain the high quality of this fleece, it should be stored and converted in a climate of 30 – 65 % relative humidity and at temperatures of 10 – 30 °C (50 – 86 °F).

After pasteing the wall with a standard wallpaper paste, the wallpaper can be hung just like all other fleece wallpapers. Thanks to its structure, it is easy to remove again and requires no additional protection.

The values provided on this datasheet are only for orientation.

Before using our media please check its compatibility for your printer and intended application. Technical specifications are subject to change, therefore we do not take responsibility for any misprints resulting from technically modified inks and/ or printers. 04.06.2012